

## LEVDEC PLUS

### Standard Colour Chart



The applied colours may differ slightly from the examples shown above. Contact our customer services for a true colour sample or a special colour match. Special corporate colours and designs can be produced to special order.

### DESCRIPTION

Levdec Plus is a medium to heavy duty epoxy resin floor finish providing an anti slip surface. The incorporation of abrasion resistant fillers in the epoxy resin produces a floor finish with the highest order of wear resistance. Levdec can be applied at thicknesses from 2mm – 3mm.

### COMPOSITION

3 pack solvent free epoxy resin and graded quartz aggregates.

### DURABILITY

Levdec exhibits the highest order of abrasion resistance. Subject to UV degradation of colour relevant to propensity of UV and colour of product.

### THICKNESS

2-4mm

### TYPICAL INSTALLATIONS

Levdec Plus is ideal for areas subject to heavy wear such as :-

- ◆ Storage areas
- ◆ Garage Floors,
- ◆ Dry Processing,
- ◆ Engineering,
- ◆ Laboratories etc.

## LEVDEC PLUS TECHNICAL DATA

### Temperature Resistance

Levdec is resistant to cleaning up to 60°C.

Typical Properties, 28 days at 20 °C

BS 8204-6 Type 5

Adhesion to concrete (BS EN 1504-2) > 1.5 MPa  
(concrete failure)

Mixed density 1.8 kg/litre

Shore D hardness 72

Slip Resistance (BS 7976-2) Dry > 40 Low Slip Potential. The typical physical properties given above are derived from testing in a controlled laboratory environment. Results derived from testing field applied samples may vary dependent upon site conditions.

Cure Schedule at 20 °C, Working life of full packs \* 25 minutes.

\* Usable working life of material following mixing and immediate spreading as per the application instructions.

### Finished floor \*

Cure time to light pedestrian traffic 24 hours

Cure time to heavy duty traffic 48 hours

Full chemical resistance 7 days

\* The above cure times are approximate and given as a guide only.

These times can vary due to prevailing site conditions.

Pack Size, 30.5 kg Coverage\*

3.6 kg/m<sup>2</sup> at 2 mm or 5.4 kg/m<sup>2</sup> at 3 mm

\* Coverage figures given are theoretical. Practical coverage rates may vary due to wastage factors and the type, condition, profile and porosity of the substrate. Application Conditions Ideal ambient and substrate temperature range is 15—25 °C. Localised heating (electric powered warm air blower) or cooling equipment may be required outside this range to achieve ideal temperature conditions. The aggregate can be stored in a cool area (or warm area in the case of low ambient temperature) in order to control product temperature and working life. The substrate and uncured floor must be kept at least 3 °C above the dew point to reduce the risk of condensation or blooming on the surface, from before priming to at least 48 hours after application. The surface strength of the concrete base or screed assessed using a rebound hammer in accordance with BS 1881-202 should be above 25 and the surface tensile strength should exceed 1.5 N/mm<sup>2</sup>. An effective structural damp proof membrane should be present and the relative humidity at the surface no more than 75% when measured by the method of BS 8203. New concrete should be a minimum of Grade C35 with a minimum cement content of 300 kg/m<sup>3</sup> and should not contain a water repellent admixture.

Surface Preparation Inadequate preparation will lead to loss of adhesion and failure. In flow applied systems there is a tendency for the finish to mirror imperfections in the substrate. Grinding, or light vacuum-contained shot-blasting is therefore preferred over planing for these systems. Percussive scabbling or acid etching is not recommended. The substrate should be finished to a surface regularity when tested according to BS 8204-1 of class SR1 otherwise a scratch coat will be required.

### Cleaning

Regular cleaning is essential to enhance and maintain the life expectancy, slip resistance and appearance of the floor. Levdec can be easily cleaned using industry standard cleaning chemicals and techniques. Consult your cleaning chemical and equipment supplier for more information.

### Storage

Materials should be kept dry and stored in a weather-proof building maintained at 15 °C to 20 °C on pallets and away from walls. Consignments should be used in order of batch number. Protect from frost.

### Shelf Life \*

12 months if stored in accordance with the above recommendations.

### Limitations

Do not proceed with application if atmospheric relative humidity is, or is anticipated to be, >80% or if the surface temperature is <3 °C above the dew point. Application should not commence when the substrate temperature or the ambient temperature is, or is anticipated to be <5 °C during the application or within the curing period. The manufacture of Levdec is a batch process and despite close manufacturing tolerances, minor variations in shade may occur between batches. Products from different batches should not be used on the same surface or surfaces close together. If mixed batches are unavoidable, it is best practice to use the different batches only in areas where the colour cannot be directly compared. Touching up should only be attempted using product from the same batch using the same application methods. Product should be reserved specially for this purpose. It is recommended that touching up is carried out up to a break in the floor or surface.

Levdec is not colour fast and may yellow over time. The rate of change will depend on UV light and heat levels and cannot be predicted. This will be more pronounced with lighter colours and blue shades and does not compromise the product's performance or chemical resistance characteristics.

### Technical Advice

For further information on this or any other Quattro Contracting product, please contact our office on 01768 868004.